

AURORA®

SPECIFICATIONS

Composition	Average Thickness	Q Carrier	Certifications
PU	200 microns	adhesive Polyester	REACH compliant VEGANOK AZIENDA N. 1004



APPLICATION INSTRUCTIONS

⊘ APPLIES ON	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated	Blade	<u></u> Pressure	>> Speed	Time	Temperature	Pressure	Peel
and dye sublimated textiles)	60°	100 gf	25 cm/sec	15 seconds	150°C (302°F)	medium (3 bar)	cold

- → Mirror cut the design
- → Weed excess material
- → Place the design on the garment
- → Heat apply at the conditions shown above
- \rightarrow Peel carrier cold

PRODUCT HIGHLIGHTS

- → Shimmering look, with glossy finish
- \rightarrow Iridescent colors
- → Structured surface



NOTE: We highly recommend to perform a test, before launching a production!

CARE AND WASHING RECOMMENDATIONS

W Washing	Ironing	Tumble dry	Ory cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	
Up to 60°C, best inside-out	YES best inside - out	YES (synthetic cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- → Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents

This document can be subject to variations. Updated versions are available on www.siser.com. For further information, please contact our sales office: info@siser.it



Siser s.r.l. Viale della Tecnica, 18 36100 Vicenza - Italy Tel. +39 0444.287960 Fax +39 0444.287959 info@siser.it www.siser.com r.e.a. vi 171856 reg. imp. vi n° 14971 c.s. € 103.300 i.v. p.iva 01591490246



